



Produktdatenblatt Fritte E 10 560

Segeformel

Na ₂ O	0,10	Al ₂ O ₃	0,30	SiO ₂	3,30
K ₂ O	0,20			B ₂ O ₃	1,00
CaO	0,70				

Chemische Zusammensetzung (typisch)

Na ₂ O	1,5
K ₂ O	6
CaO	10
Al ₂ O ₃	10
B ₂ O ₃	19
SiO ₂	53,5

Andere Kennwerte

WAK _(20-400°C) :	66,00	x 10 ⁻⁷ K ⁻¹
DEP:	685,00	°C