



Produktdatenblatt Fritte M 4067

Segeformel

K ₂ O	0,10	Al ₂ O ₃	0,10	SiO ₂	1,00
ZnO	0,30				
BaO	0,50				
PbO	0,10				

Molmasse: 203,0 g/mol

Chemische Zusammensetzung (typisch) [%]

K ₂ O	4,60
ZnO	12,00
BaO	37,80
PbO	11,00
Al ₂ O ₃	5,00
SiO ₂	29,60

Andere Kennwerte

WAK _(20-400°C) :	119,00	x 10 ⁻⁷ K ⁻¹
DEP:	>870	°C